

# DIVERSIFIED

TESTING LABORATORIES, INC.  
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET  
P.O. BOX 4004  
BURLINGTON, NORTH CAROLINA 27215  
PHONE (336) 227-7710 • FAX (336) 227-1175  
www.diversifiedtestinglabs.com

April 4, 2013

Mr. Joseph Daniels  
ECOFABRIX  
34-26 41<sup>st</sup> Street  
Long Island City, NY 11101

Reference: Laboratory Test Report  
Lab Identification No. 5830  
Invoice No. 36538 (Attached)

Dear Mr. Daniels:


One (1) fabric sample, identified as **255**, was received and tested in accordance with the National Fire Prevention Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2010 Edition, (Test 1, Small Scale)". The results are as follows:

<u>Specimen Number</u>	<u>Residual Flame (seconds)</u>	<u>Weight Loss (percent)</u>
1	0.0	24.52
2	0.0	0.51
3	0.0	16.32
4	0.0	22.07
5	0.0	15.39
6	0.0	4.11
7	0.0	23.90
8	0.0	25.57
9	0.0	22.41
10	<u>0.0</u>	<u>26.60</u>
AVG.	0.0	18.14

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,



Brian S. Dement

BSD/mr  
Attachment