

DIVERSIFIED

TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

"We Test Per Your Request"

January 25, 2013

Mr. Joseph Daniels
ECOFABRIX
34-26 41st Street
Long Island City, NY 11101

Reference: Laboratory Test Report
Lab Identification No. 5098
Invoice No. 35802 (Attached)

Dear Mr. Daniels:

One (1) fabric sample, identified as 450, was received and tested in accordance with the National Fire Prevention Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2010 Edition, (Test 1, Small Scale)". The results are as follows:

<u>Specimen Number</u>	<u>Residual Flame (seconds)</u>	<u>Weight Loss (percent)</u>
1	0.0	3.74
2	0.0	20.24
3	0.0	2.32
4	0.0	20.22
5	0.0	0.27
6	0.0	19.87
7	8.0	15.84
8	0.0	19.08
9	0.0	17.73
10	<u>8.0</u>	<u>19.90</u>
AVG.	1.6	13.93

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,



Bobby E. Puett

BEP/mr
Attachment