



# DIVERSIFIED

TESTING LABORATORIES, INC.  
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET  
P.O. BOX 4004  
BURLINGTON, NORTH CAROLINA 27215  
PHONE (336) 227-7710 • FAX (336) 227-1175  
www.diversifiedtestinglabs.com

January 25, 2013

Mr. Joseph Daniels  
ECOFABRIX  
34-26 41<sup>st</sup> Street  
Long Island City, NY 11101

Reference: Laboratory Test Report  
Lab Identification No. 5098  
Invoice No. 35802 (Attached)

Dear Mr. Daniels:

One (1) fabric sample, identified as **455**, was received and tested in accordance with the California Administrative Code Title 19-- Public Safety, Section 1237. Flame Resistance, Small Scale Test. The results are as follows:

<u>Specimen Number</u>	<u>After Flame Time (sec)</u>		<u>Char Length (in)</u>	
	<u>Length</u>	<u>Width</u>	<u>Length</u>	<u>Width</u>
1	0.0	0.0	2.9	2.3
2	0.0	0.0	2.3	2.3
3	0.0	0.0	2.7	2.4
4	0.0	0.0	2.4	2.2
5	<u>0.0</u>	<u>0.0</u>	2.7	2.6
Avg.	0.0	0.0		

The sample submitted, in its original state, **meets** the minimum requirements of the above standard. The char length may not exceed 6.0 inches for any individual specimen and the average afterflame time may not exceed 4.0 seconds in the length or width directions.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett

BEP/mr  
Attachment