


DIVERSIFIED
TESTING LABORATORIES, INC.

WORLDWIDE SERVICE



“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

December 9, 2015

Ms. Dara Centonze
ECOFABRIX
77 Second Avenue
Garden City Park, NY 11040

Reference: Laboratory Test Report
Lab Identification No. 17775
Invoice No. 48644 (Attached)

Dear Ms. Centonze:

One (1) fabric sample, identified as 700, was received and tested in accordance with the California Administrative Code Title 19-- Public Safety, Section 1237. Flame Resistance, Small Scale Test. The results are as follows:

<u>Specimen Number</u>	<u>After Flame Time (sec)</u>		<u>Char Length (in)</u>	
	<u>Length</u>	<u>Width</u>	<u>Length</u>	<u>Width</u>
1	0.0	0.0	3.4	3.6
2	0.0	0.0	2.9	3.2
3	0.0	0.0	3.1	3.4
4	0.0	0.0	3.2	3.1
5	0.0	0.0	4.2	2.8
Avg.	0.0	0.0		

The sample submitted, in its original state, **meets** the minimum requirements of the above standard. The char length may not exceed 6.0 inches for any individual specimen and the average afterflame time may not exceed 4.0 seconds in the length or width directions.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett

BEP/mr
Attachment