



**DIVERSIFIED**  
TESTING LABORATORIES, INC.  
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET  
P.O. BOX 4004  
BURLINGTON, NORTH CAROLINA 27215  
PHONE (336) 227-7710 • FAX (336) 227-1175  
www.diversifiedtestinglabs.com

December 9, 2015

Ms. Dara Centonze  
ECOFABRIX  
77 Second Avenue  
Garden City Park, NY 11040

Reference: Laboratory Test Report  
Lab Identification No. 17775  
Invoice No. 48644 (Attached)

Dear Ms. Centonze:

One (1) fabric sample, identified as 363, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2015 Edition, (Test 1, Small Scale)". The results are as follows:

<u>Specimen Number</u>	<u>Residual Flame</u> ( <u>seconds</u> )	<u>Weight Loss</u> ( <u>percent</u> )
1	0.0	2.66
2	0.0	2.74
3	0.0	2.74
4	0.0	3.09
5	0.0	2.50
6	0.0	2.45
7	0.0	2.56
8	0.0	2.78
9	0.0	2.52
10	0.0	2.25
AVG.	0.0	2.63

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett

BEP/mr  
Attachment