



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

December 6, 2019

Ms. Dara Centonze
WT SHADE
77 Second Avenue
Garden City Park, NY 11040

Reference: Flammability Test Report
Lab Identification No. 39163
Invoice No. 70383

Dear Ms. Centonze:

One (1) fabric sample, identified as **ITEM 784-10 – ECOFABRIX 784 BLACKOUT / WHITE**, was received and tested in accordance with CAN/ULC-S109-14, “Standard for Flame Tests of Flame-Resistant Fabrics and Films”, Small-Flame Test. The results are as follows:

<u>Specimen Number</u>	<u>Test Results</u>		<u>Damaged Length (mm)</u>	
	<u>Residual Flame (sec)</u>		<u>Warp</u>	<u>Fill</u>
	<u>Warp</u>	<u>Fill</u>	<u>Warp</u>	<u>Fill</u>
1	0.0	0.0	86	79
2	0.0	0.0	89	99
3	0.0	0.0	102	86
4	0.0	0.0	102	76
5	0.0	0.0	99	91
Avg.			91	

The fabric sample submitted **meets** the minimum requirements of the Small-Flame Test. The maximum average damaged length shall not exceed 165 millimeters and the maximum damaged length for any individual specimen shall not exceed 190 millimeters. No residues shall fall to the floor of the test chamber and continue flaming for more than two (2) seconds at any time during the test.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

December 6, 2019

Ms. Dara Centonze
WT SHADE
77 Second Avenue
Garden City Park, NY 11040

Reference: Flammability Test Report
Lab Identification No. 39163
Invoice No. 70383

Dear Ms. Centonze:

One (1) fabric sample, identified as **ITEM 784-10 – ECOFABRIX 784 BLACKOUT / WHITE**, was received and tested in accordance with CAN/ULC-S109-14, “Standard for Flame Tests of Flame-Resistant Fabrics and Films”, Large-Flame Test. The results are as follows:

Test Results

<u>Specimen Number</u>	<u>Residual Flame (Seconds)</u>	<u>Char Length (Millimeters)</u>
Length 1	0.0	102
Length 2	0.0	114
Width 1	0.0	102
Width 2	0.0	102

The fabric sample submitted **meets** the minimum requirements of the Large-Flame Test. The length of char on the individual folded specimens shall not exceed 635 millimeters. No residues shall fall to the floor of the test chamber and continue flaming for more than two (2) seconds at any time during the test.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

